

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G301-1

Certified Control Values

50 gram Fire Assay

Gold Grade 0.85 ppm
Standard Deviation 0.05 ppm
Confidence Interval +/- 0.01 ppm

Aqua Regia Digest

Gold Grade 0.83 ppm
Standard Deviation 0.10 ppm
Confidence Interval +/- 0.026 ppm



CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	Control statistics were produced from results accumulated in the April-2001 round robin. A total of 91 fire assay results and 55 results from an aqua regia technique were used to certify this material.	Antimony	<0.2	Fe
<u>Material Description</u> This material is described as a Gold Ore ex Eastern Goldfields.	Arsenic	<1	SiO ₂	nr
	Barium	<100	Al ₂ O ₃	nr
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light gray in colour.	Bromine	<1	TiO ₂	nr
	Cadmium	nr	MnO	nr
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	<1	CaO	nr
	Calcium (%)	5.94	P	nr
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	34.5	S	nr
	Chromium	181	MgO	nr
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	36.2	K ₂ O	nr
	Europium	1.84	Na ₂ O	nr
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	840	LOI1000	nr
	Hafnium	3.16	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
Iridium (ppb)	<20			
<u>Material Safety</u> This product is not hazardous and non-toxic.	Iron (%)	8.53	'nr': Not Reported	
	Lanthanum	11.9		
	Lutetium	0.38		
	Mercury	nr		
	Molybdenum	<5		
	Neodymium	nr		
	Nickel	nr		
	Potassium (%)	0.74		
	Rubidium	35.6		
	Samarium	5.34		
	Scandium	33.2		
	Selenium	<5		
	Silver	<5		
	Sodium (%)	2.34		
	Strontium	nr		
	Tantalum	<1		
	Tellurium	<5		
	Terbium	nr		
	Thorium	1.37		
	Tin	nr		
	Tungsten	<2		
	Uranium	<2		
	Ytterbium	2.99		
	Zinc	175		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

G301-1

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: