

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G306-4

Certified Control Values

50 gram Fire Assay

Gold Grade 21.57 ppm
Standard Deviation 0.78 ppm
Confidence Interval +/- 0.164 ppm

Aqua Regia Digest

Gold Grade 21.73 ppm
Standard Deviation 1.40 ppm
Confidence Interval +/- 0.446 ppm



CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
Control statistics were produced from results accumulated in the April-2006 round robin. A total of 90 fire assay results and 41 results from an aqua regia technique were used to certify this material.	Antimony	8.2	Fe	nr
	Arsenic	449	SiO ₂	nr
	Barium	140	Al ₂ O ₃	nr
	Bromine	<0.5	TiO ₂	nr
	Cadmium	nr	MnO	nr
	Caesium	39	CaO	nr
	Calcium (%)	nr	P	nr
	Cerium	15	S	nr
	Chromium	210	MgO	nr
	Cobalt	42	K ₂ O	nr
	Europium	0.9	Na ₂ O	nr
	Gold (ppb)	22500	LOI1000	nr
	Hafnium	2		
	Iridium (ppb)	<13	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Iron (%)	6.78	nr: Not Reported	
	Lanthanum	8		
	Lutetium	0.3		
	Mercury	nr		
	Molybdenum	28		
	Neodymium	nr		
	Nickel	170		
	Potassium (%)	nr		
	Rubidium	860		
	Samarium	3.6		
	Scandium	24.3		
	Selenium	<3		
	Silver	26.9		
	Sodium (%)	1.91		
	Strontium	nr		
	Tantalum	0.9		
	Tellurium	nr		
	Terbium	<0.5		
	Thorium	0.7		
	Tin	<100		
	Tungsten	6		
	Uranium	<0.5		
	Ytterbium	2.3		
	Zinc	194		
	Zirconium	nr		
<u>Material Description</u> This material is described as a High Grade oxide ore (trace-low Sulphide).				
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light brownish gray in colour.				
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.				
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.				
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.				
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.				
<u>Material Safety</u> This product is not hazardous and non-toxic.				

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

G306-4

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: