

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G310-3

Certified Control Values

50 gram Fire Assay

Gold Grade 0.07 ppm
Standard Deviation 0.02 ppm
Confidence Interval +/- 0.003 ppm

Aqua Regia Digest

Gold Grade 0.06 ppm
Standard Deviation 0.02 ppm
Confidence Interval +/- 0.006 ppm



CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
Control statistics were produced from results accumulated in the April-2010 round robin. A total of 110 fire assay results and 49 results from an aqua regia technique were used to certify this material.	Antimony	0.803	Fe	nr
	Arsenic	1	SiO ₂	nr
	Barium	340	Al ₂ O ₃	nr
	Bromine	0.6	TiO ₂	nr
	Cadmium	<5	MnO	nr
	Caesium	2	CaO	nr
	Calcium (%)	nr	P	nr
	Cerium	34.8	S	nr
	Chromium	110	MgO	nr
	Cobalt	29.9	K ₂ O	nr
	Europium	1.45	NazO	nr
	Gold (ppb)	65	LOI1000	nr
	Hafnium	4.04		
	Iridium (ppb)	<5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Iron (%)	6.73	nr: Not Reported	
	Lanthanum	17.8		
	Lutetium	0.452		
	Mercury	nr		
	Molybdenum	6		
	Neodymium	nr		
	Nickel	<100		
	Potassium (%)	nr		
	Rubidium	80		
	Samarium	4.64		
	Scandium	24.9		
	Selenium	<1.5		
	Silver	<1.9		
	Sodium (%)	2.33		
	Strontium	nr		
	Tantalum	1.23		
	Tellurium	<3.6		
	Terbium	0.89		
	Thorium	10.1		
	Tin	<100		
	Tungsten	1		
	Uranium	4.5		
	Ytterbium	2.83		
	Zinc	109		
	Zirconium	<500		
Material Description This material is described as a Very low grade waste .				
Colour Designation (ISCC-NBS, SP440) This material is light brownish gray in colour.				
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.				
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.				
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.				
Stability This product remains stable in its original packaging, away from direct sunlight.				
Material Safety This product is not hazardous and non-toxic.				

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

G310-3

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: