

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G312-6

Certified Control Values

50 gram Fire Assay

Gold Grade 2.42 ppm
Standard Deviation 0.10 ppm
Confidence Interval +/- 0.015 ppm

Aqua Regia Digest

Gold Grade 2.42 ppm
Standard Deviation 0.12 ppm
Confidence Interval +/- 0.028 ppm



CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	Control statistics were produced from results accumulated in the April-2012 round robin. A total of 157 fire assay results and 68 results from an aqua regia technique were used to certify this material.	Antimony	0.851	Fe
<u>Material Description</u> This material is described as an Oxide Gold Ore.	Arsenic	<0.5	SiO ₂	61.96
	<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light brownish gray in colour.	Barium	510	Al ₂ O ₃
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.		Bromine	0.893	TiO ₂
	<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<10	MnO
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.		Caesium	3	CaO
	<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P
<u>Material Safety</u> This product is not hazardous and non-toxic.		Cerium	40	S
	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>	Chromium	90	MgO
<u>Major Elements by Fusion / XRF (%)</u>		Cobalt	21.7	K ₂ O
		Europium	1.2	NazO
		Gold (ppb)	2500	LOI1000
		Hafnium	3.7	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.
		Iridium (ppb)	<10	nr: Not Reported
		Iron (%)	5.2	
		Lanthanum	24	
		Lutetium	0.4	
		Mercury	nr	
		Molybdenum	<5	
		Neodymium	nr	
		Nickel	30	
		Potassium (%)	nr	
		Rubidium	120	
		Samarium	4.1	
		Scandium	18.2	
		Selenium	<5	
		Silver	2	
		Sodium (%)	2.6	
		Strontium	nr	
		Tantalum	1.1	
		Tellurium	<10	
		Terbium	0.6	
		Thorium	15.3	
		Tin	<100	
		Tungsten	4	
		Uranium	8.1	
		Ytterbium	2.33	
		Zinc	89	
		Zirconium	<200	

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

G312-6

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: