

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G900-10

Certified Control Values

50 gram Fire Assay

Gold Grade 13.85 ppm
Standard Deviation 0.53 ppm
Confidence Interval +/- 0.121 ppm

Aqua Regia Digest

Gold Grade 13.85 ppm
Standard Deviation 0.70 ppm
Confidence Interval +/- 0.204 ppm



CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	<u>Analysis Results (ppm, unless otherwise noted)</u>			
Control statistics were produced from results accumulated in the October-2000 round robin. A total of 79 fire assay results and 49 results from an aqua regia technique were used to certify this material.	Antimony	1.14	Fe	nr
	Arsenic	59	SiO ₂	nr
	Barium	<100	Al ₂ O ₃	nr
	Bromine	<1	TiO ₂	nr
	Cadmium	nr	MnO	nr
	Caesium	39.5	CaO	nr
	Calcium (%)	2.11	P	nr
	Cerium	14.6	S	nr
	Chromium	82.4	MgO	nr
	Cobalt	22.6	K ₂ O	nr
	Europium	0.69	Na ₂ O	nr
	Gold (ppb)	13800	LOI1000	nr
	Hafnium	4.7	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes. 'nr': Not Reported	
	Iridium (ppb)	<20		
	Iron (%)	3.52		
	Lanthanum	6.18		
	Lutetium	<0.2		
	Mercury	nr		
	Molybdenum	<5		
	Neodymium	nr		
	Nickel	nr		
	Potassium (%)	5.49		
	Rubidium	1400		
	Samarium	2.48		
	Scandium	11.1		
	Selenium	<5		
	Silver	<5		
	Sodium (%)	2.69		
	Strontium	nr		
	Tantalum	<1		
	Tellurium	<5		
	Terbium	nr		
	Thorium	0.76		
	Tin	nr		
	Tungsten	2.75		
	Uranium	<2		
	Ytterbium	1.41		
	Zinc	<100		
	Zirconium	<500		
<u>Material Description</u> This material is described as a High Grade ore in the Eastern Goldfields Minor sulphide.				
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light olive gray in colour.				
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.				
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.				
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.				
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.				
<u>Material Safety</u> This product is not hazardous and non-toxic.				

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

G900-10

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: