

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G905-9

Certified Control Values

50 gram Fire Assay

Gold Grade 1.86 ppm
Standard Deviation 0.07 ppm
Confidence Interval +/- 0.016 ppm

Aqua Regia Digest

Gold Grade 1.73 ppm
Standard Deviation 0.22 ppm
Confidence Interval +/- 0.071 ppm



CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	<u>Analysis Results (ppm, unless otherwise noted)</u>			
Control statistics were produced from results accumulated in the October-2005 round robin. A total of 84 fire assay results and 39 results from an aqua regia technique were used to certify this material.	Antimony	1.6	Fe	nr
	Arsenic	153	SiO ₂	nr
	Barium	170	Al ₂ O ₃	nr
	Bromine	7.7	TiO ₂	nr
	Cadmium	<5	MnO	nr
	Caesium	41	CaO	nr
	Calcium (%)	nr	P	nr
	Cerium	18	S	nr
	Chromium	470	MgO	nr
	Cobalt	48	K ₂ O	nr
	Europium	<1	Na ₂ O	nr
	Gold (ppb)	1913.333	LOI1000	nr
	Hafnium	<1	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	'nr': Not Reported
	Iridium (ppb)	<50		
	Iron (%)	16		
	Lanthanum	11		
	Lutetium	<0.2		
	Mercury	nr		
	Molybdenum	3		
	Neodymium	nr		
	Nickel	240		
	Potassium (%)	nr		
	Rubidium	74		
	Samarium	2.2		
	Scandium	12		
	Selenium	<5		
	Silver	<2		
	Sodium (%)	0.89		
	Strontium	nr		
	Tantalum	2		
	Tellurium	<10		
	Terbium	<0.5		
	Thorium	2.8		
	Tin	<100		
	Tungsten	14		
	Uranium	1.2		
	Ytterbium	<2		
	Zinc	320		
	Zirconium	<200		
<u>Material Description</u> This material is described as a Sulphide ore ex Southern Cross W.A.				
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is medium gray in colour.				
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.				
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.				
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.				
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.				
<u>Material Safety</u> This product is not hazardous and non-toxic.				

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

G905-9

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: