

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G915-2


Certified Control Values

50 gram Fire Assay

Gold Grade 4.98 ppm
Standard Deviation 0.19 ppm
Confidence Interval +/- 0.02 ppm

Aqua Regia Digest

Gold Grade 4.94 ppm
Standard Deviation 0.20 ppm
Confidence Interval +/- 0.038 ppm



CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the October-2015 & October-2017 round robins. A total of 349 fire assay results and 110 results from an aqua regia technique were used to certify this material.	Antimony	0.205	Fe
Material Description This material is described as a Run of mine gold ore composite .	Arsenic	<0.5	SiO ₂	52.79
Colour Designation (ISCC-NBS, SP440) This material is medium light gray in colour.	Barium	134.5	Al ₂ O ₃	14.06
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Bromine	<2	TiO ₂	2.02
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<10	MnO	0.18
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Caesium	<1	CaO	8.69
Stability This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P	0.086
Material Safety This product is not hazardous and non-toxic.	Cerium	27.15	S	0.044
	Chromium	156	MgO	4.96
	Cobalt	40.5	K ₂ O	0.7
	Europium	1.78	NazO	nr
	Gold (ppb)	5330	LOI1000	-0.26
	Hafnium	<5		
	Iridium (ppb)	<50		
	Iron (%)	8.95		
	Lanthanum	12.5		
	Lutetium	0.475		
	Mercury	nr		
	Molybdenum	<10		
	Neodymium	nr		
	Nickel	43		
	Potassium (%)	nr		
	Rubidium	<20		
	Samarium	5.55		
	Scandium	32.6		
	Selenium	<10		
	Silver	10		
	Sodium (%)	2.295		
	Strontium	nr		
	Tantalum	<2		
	Tellurium	<20		
	Terbium	1		
	Thorium	3.53		
	Tin	<200		
	Tungsten	<5		
	Uranium	2		
	Ytterbium	3.35		
	Zinc	130		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

G915-2

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: