

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Gold Reference Material Product Code

G915-5


Certified Control Values

50 gram Fire Assay

Gold Grade 17.95 ppm
Standard Deviation 0.86 ppm
Confidence Interval +/- 0.13 ppm

Aqua Regia Digest

Gold Grade 17.29 ppm
Standard Deviation 1.21 ppm
Confidence Interval +/- 0.327 ppm



CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the October-2015 round robin. A total of 172 fire assay results and 56 results from an aqua regia technique were used to certify this material.	Antimony	816	Fe
Material Description This material is described as a High grade gold Cu Pb Zn ore some sulphide.	Arsenic	1300	SiO ₂	51.08
Colour Designation (ISCC-NBS, SP440) This material is medium dark gray in colour.	Barium	480	Al ₂ O ₃	11.44
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Bromine	<2	TiO ₂	1.38
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	46.7	MnO	0.15
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Caesium	<1	CaO	5.28
Stability This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P	0.066
Material Safety This product is not hazardous and non-toxic.	Cerium	37.8	S	3.825
	Chromium	70	MgO	2.91
	Cobalt	115	K ₂ O	1.65
	Europium	1.49	NazO	nr
	Gold (ppb)	16900	LOI1000	2.59
	Hafnium	<5		
	Iridium (ppb)	<50		
	Iron (%)	8.9		
	Lanthanum	20		
	Lutetium	0.4		
	Mercury	nr		
	Molybdenum	84.7		
	Neodymium	nr		
	Nickel	190		
	Potassium (%)	nr		
	Rubidium	75		
	Samarium	4.6		
	Scandium	19.6		
	Selenium	20		
	Silver	48		
	Sodium (%)	2		
	Strontium	nr		
	Tantalum	2		
	Tellurium	<20		
	Terbium	<1		
	Thorium	9.99		
	Tin	<200		
	Tungsten	13		
	Uranium	5		
	Ytterbium	3		
	Zinc	19200		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

G915-5

Geostats Pty Ltd, Certified Gold Reference Material, Product Code: