# **GEOSTATS PTY LTD**

Mining Industry Consultants
Reference Material Manufacture and Sales

#### **Certified Bauxite Reference Material**

# **GBAP-6**

### **Certified Control Values**

**Bauxite Analyses** 

Element	Units	Grade	Standard	No of Analyses	95% Confidence
			Deviation		Interval
SiO2	%	4.41	0.046	40	+/- 0.014
AI2O3	%	56.0	0.27	40	+/- 0.084
Fe2O3	%	6.8	0.07	40	+/- 0.022
P2O5	%	0.053	0.0047	30	+/- 0.002
TiO2	%	3.54	0.044	40	+/- 0.014
ZrO2	%	0.207	0.0138	20	+/- 0.006
V2O5	%	0.031	0.0089	20	+/- 0.004
Cr2O3	%	0.033	0.0045	30	+/- 0.002
LOI	%	28.8	0.11	38	+/- 0.035

#### **CRM Details**

## **Control Statistic Details**

Control values for this material were determined during a certification progra

#### **Certification Date**

This material was certified with the above values on: May 2006

# Source Material

Prior to homogenisation and testing, this material was sourced from: Gove Peninsula, Northern Territory

#### **Material Type**

Pulp Bauxite

#### <u>Usage</u>

This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.

# Preparation and Packaging

This standard was dried in an oven for a minimum of 12 hours at 110oC. The dry material was then blended in a vee blender approximately 12 hours. The material is then stored in a sealed, stable container ready for final packaging.

Materials are statistically sampled from stores, then packaged into heat sealed, air tight, plastic packets ready for distribution packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.

#### **Assay Testwork**

This standard was tested in a dedicated certification program. 10, 10g samples were sent to 4 laboratories for XRF and ICP analyses. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.

Non-certified values **Element** CaO <0.02 K20 0.011 MgO 0.039 SO3 0.100 MnO <0.01 0.011 BaO 0.010 Na<sub>2</sub>O

10A Marsh Close, O'Connor, Western Australia 6163
Phone: +61 8 9314 2566, Fax: +61 8 9314 3699
e-mail: pjh@geostats.com.au, srr@geostats.com.au
Website http://www.geostats.com.au