


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Ore Grade Base Metal Reference Material Product Code

GBM310-11

Certified Control Values



GBM310-11

Geostats Pty Ltd, Certified Ore Grade Base Metal Reference Material, Product Code:

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	21031	1095	155	+/- 174
Copper (ppm)	11494	458	189	+/- 66
Zinc (ppm)	141	nr	nr	nr
Lead (ppm)	38	nr	nr	nr
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	3.5	0.6	85	+/- 0.14
Sulphur (%)	17.62	0.71	133	+/- 0.12

CRM Details

<u>Control Statistic Details</u> Control statistics were produced from results accumulated in the April-2010 & April-2013 round robins. The number of results used to certify each analyte is shown in the table above.	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	<u>Material Description</u> This material is described as a Nickel Sulphide ore.	Antimony	0.69	Fe
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is dark gray in colour.	Arsenic	3.2	SiO ₂	nr
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Barium	330.5	Al ₂ O ₃	nr
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Bromine	<1.1	TiO ₂	nr
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cadmium	<5	MnO	nr
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Caesium	2.1	CaO	nr
<u>Material Safety</u> This product is not hazardous and non-toxic.	Calcium (%)	nr	P	nr
	Cerium	30.5	S	nr
	Chromium	56.85	MgO	nr
	Cobalt	1017.5	K ₂ O	nr
	Europium	0.74	Na ₂ O	nr
	Gold (ppb)	33.9	LOI1000	nr
	Hafnium	2.655		
	Iridium (ppb)	<5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Iron (%)	32.95	'nr': Not Reported	
	Lanthanum	19.75		
	Lutetium	0.23		
	Mercury	nr		
	Molybdenum	<1		
	Neodymium	nr		
	Nickel	22100		
	Potassium (%)	nr		
	Rubidium	48.75		
	Samarium	2.99		
	Scandium	8.04		
	Selenium	47.25		
	Silver	3		
	Sodium (%)	0.558		
	Strontium	nr		
	Tantalum	0.583		
	Tellurium	<6.1		
	Terbium	0.466		
	Thorium	6.4		
	Tin	<100		
	Tungsten	<3		
	Uranium	<0.5		
	Ytterbium	1.39		
	Zinc	<50		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>