


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM313-8

Certified Control Values



GBM313-8

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	35	5	54	+/- 1.4
Copper (ppm)	58	8	59	+/- 2.1
Zinc (ppm)	114	9	54	+/- 2.4
Lead (ppm)	6	3	35	+/- 1.2
Arsenic (ppm)	2	nr	nr	nr
Cobalt (ppm)	36	3	51	+/- 0.8
Silver (ppm)	0.4	nr	nr	nr

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	9	2	32	+/- 0.6
Copper (ppm)	50	5	59	+/- 1.4
Zinc (ppm)	51	4	41	+/- 1.2
Lead (ppm)	3	nr	nr	nr
Arsenic (ppm)	2	nr	nr	nr
Cobalt (ppm)	17	10	48	+/- 2.9
Silver (ppm)	0.6	nr	nr	nr

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the April-2013 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony	<0.0739	Fe
Material Description This material is described as a Fresh Bunbury Basalt.	Arsenic	<1.39	SiO ₂	51.82
	Barium	132	Al ₂ O ₃	14.73
Colour Designation (ISCC-NBS, SP440) This material is medium light gray in colour.	Bromine	<0.781	TiO ₂	1.897
	Cadmium	<4.91	MnO	0.16
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	0.243	CaO	9.68
	Calcium (%)	nr	P	0.091
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	19.9	S	0.055
	Chromium	159	MgO	5.47
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	39.6	K ₂ O	0.388
	Europium	1.84	Na ₂ O	2.928
Stability This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	<2.13	LOI1000	0.32
	Hafnium	3.84	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
Material Safety This product is not hazardous and non-toxic.	Iridium (ppb)	<7.88	'nr': Not Reported	
	Iron (%)	8.68		
	Lanthanum	9.48		
	Lutetium	0.438		
	Mercury	nr		
	Molybdenum	<0.606		
	Neodymium	nr		
	Nickel	43		
	Potassium (%)	nr		
	Rubidium	7.35		
	Samarium	5.32		
	Scandium	26.9		
	Selenium	<1.74		
	Silver	<1		
	Sodium (%)	2.22		
	Strontium	nr		
	Tantalum	0.502		
	Tellurium	<2.36		
	Terbium	1		
	Thorium	1.22		
	Tin	<36.3		
	Tungsten	<4.03		
	Uranium	<0.263		
	Ytterbium	2.8		
	Zinc	150		
	Zirconium	<158		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: