


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM315-3

Certified Control Values



GBM315-3

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	21	3	64	+/- 0.7
Copper (ppm)	1205	40	73	+/- 9.5
Zinc (ppm)	77	6	65	+/- 1.5
Lead (ppm)	27	3	61	+/- 0.9
Arsenic (ppm)	4	3	17	+/- 1.3
Cobalt (ppm)	19	1	61	+/- 0.4
Silver (ppm)	2.6	0.5	61	+/- 0.12

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	9	2	54	+/- 0.5
Copper (ppm)	1222	65	84	+/- 14.3
Zinc (ppm)	46	5	66	+/- 1.2
Lead (ppm)	18	3	60	+/- 0.7
Arsenic (ppm)	3	2	15	+/- 1.2
Cobalt (ppm)	8	3	60	+/- 0.7
Silver (ppm)	2.5	0.4	64	+/- 0.09

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)	Major Elements by Fusion / XRF (%)	
		Element	Value
<p>Control statistics were produced from results accumulated in the April-2015 round robin. The number of results used to certify each analyte is shown in the table above.</p>	Antimony 0.1	Fe	4.573
<p>Material Description This material is described as a Low grade Cu / Au ore - This material also certified for partial digests.</p>	Arsenic <1	SiO ₂	64.6
	Barium 490	Al ₂ O ₃	13.75
<p>Colour Designation (ISCC-NBS, SP440) This material is light gray in colour.</p>	Bromine <0.5	TiO ₂	1.02
	Cadmium <5	MnO	0.1
<p>Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.</p>	Caesium 3.2	CaO	4.89
	Calcium (%) nr	P	0.055
<p>Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.</p>	Cerium 43	S	0.048
	Chromium 80	MgO	2.63
<p>Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.</p>	Cobalt 20	K ₂ O	2.48
	Europium 1.1	Na ₂ O	3.24
<p>Stability This product remains stable in its original packaging, away from direct sunlight.</p>	Gold (ppb) 352	LOI1000	0.43
	Hafnium 4	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
<p>Material Safety This product is not hazardous and non-toxic.</p>	Iridium (ppb) <50	'nr': Not Reported	
	Iron (%) 4.8		
	Lanthanum 26		
	Lutetium 0.2		
	Mercury nr		
	Molybdenum <2		
	Neodymium nr		
	Nickel 24		
	Potassium (%) nr		
	Rubidium 120		
	Samarium 4.6		
	Scandium 18.6		
	Selenium <10		
	Silver 3		
	Sodium (%) 2.48		
	Strontium nr		
	Tantalum 1.3		
	Tellurium nr		
	Terbium 0.8		
	Thorium 18.8		
	Tin nr		
	Tungsten <1		
	Uranium 8.3		
	Ytterbium 2		
	Zinc 64		
	Zirconium nr		

20 Hines Road, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website http://www.geostats.com.au

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: