


# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

## GBM315-6

Certified Control Values



GBM315-6

### Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	27	3	63	+/- 0.7
Copper (ppm)	45	6	68	+/- 1.6
Zinc (ppm)	91	7	64	+/- 1.6
Lead (ppm)	18	3	59	+/- 0.9
Arsenic (ppm)	2	2	11	+/- 1.4
Cobalt (ppm)	25	2	62	+/- 0.5
Silver (ppm)	1.3	0.2	53	+/- 0.05

### Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	9	2	56	+/- 0.5
Copper (ppm)	38	4	68	+/- 1.1
Zinc (ppm)	50	5	65	+/- 1.2
Lead (ppm)	14	3	64	+/- 0.8
Arsenic (ppm)	2	1	12	+/- 0.6
Cobalt (ppm)	10	3	63	+/- 0.9
Silver (ppm)	1.3	0.1	51	+/- 0.04

### CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)	Major Elements by Fusion / XRF (%)	
		Fe	5.972
Control statistics were produced from results accumulated in the April-2015 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony <0.1	SiO <sub>2</sub>	60.58
<b>Material Description</b> This material is described as a Low gold Copper ore - This material also certified for partial digests.	Arsenic <1	Al <sub>2</sub> O <sub>3</sub>	13.95
<b>Colour Designation (ISCC-NBS, SP440)</b> This material is light gray in colour.	Barium 350	TiO <sub>2</sub>	1.34
<b>Usage</b> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Bromine 0.503	MnO	0.13
<b>Preparation and Packaging</b> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium <5	CaO	6.46
<b>Assay Testwork</b> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Caesium 2.4	P	0.067
<b>Stability</b> This product remains stable in its original packaging, away from direct sunlight.	Calcium (%) nr	S	0.036
<b>Material Safety</b> This product is not hazardous and non-toxic.	Cerium 34	MgO	3.61
	Chromium 120	K <sub>2</sub> O	1.79
	Cobalt 27	Na <sub>2</sub> O	3.1
	Europium 1.3	LOI1000	0.3
	Gold (ppb) 220	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Hafnium 4	'nr': Not Reported	
	Iridium (ppb) <50		
	Iron (%) 6		
	Lanthanum 20		
	Lutetium 0.4		
	Mercury nr		
	Molybdenum 9		
	Neodymium nr		
	Nickel 30		
	Potassium (%) nr		
	Rubidium 90		
	Samarium 4.9		
	Scandium 24.3		
	Selenium <10		
	Silver <1		
	Sodium (%) 2.28		
	Strontium nr		
	Tantalum 1.1		
	Tellurium nr		
	Terbium 0.9		
	Thorium 13.9		
	Tin nr		
	Tungsten <1		
	Uranium 5.8		
	Ytterbium 2		
	Zinc 65		
	Zirconium nr		

20 Hines Road, O'Connor, Western Australia 6163  
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699  
e-mail : pjh@geostats.com.au, srr@geostats.com.au  
Website http://www.geostats.com.au

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: