


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM316-2

Certified Control Values



GBM316-2

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	41	3	71	+/- 0.8
Copper (ppm)	1523	45	75	+/- 10.4
Zinc (ppm)	1331	56	75	+/- 13
Lead (ppm)	626	21	67	+/- 5.1
Arsenic (ppm)	82	4	52	+/- 1.3
Cobalt (ppm)	35	2	64	+/- 0.5
Silver (ppm)	3.2	0.4	62	+/- 0.11

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	32	2	55	+/- 0.5
Copper (ppm)	1530	78	83	+/- 17.1
Zinc (ppm)	1303	72	71	+/- 17.1
Lead (ppm)	624	25	65	+/- 6.3
Arsenic (ppm)	83	6	64	+/- 1.4
Cobalt (ppm)	25	4	64	+/- 0.9
Silver (ppm)	3.2	0.5	73	+/- 0.11

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the April-2016 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony	52.4	Fe
Material Description This material is described as a Copper Gold Ore Sulphide.	Arsenic	83	SiO ₂	58.78
Colour Designation (ISCC-NBS, SP440) This material is medium light gray in colour.	Barium	340	Al ₂ O ₃	12.58
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Bromine	<2	TiO ₂	1.734
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<10	MnO	0.153
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Caesium	2	CaO	5.81
Stability This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P	0.097
Material Safety This product is not hazardous and non-toxic.	Cerium	42.8	S	0.342
	Chromium	<20	MgO	2.97
	Cobalt	38	K ₂ O	1.72
	Europium	1.6	Na ₂ O	2.988
	Gold (ppb)	1010	LOI1000	1.27
	Hafnium	<5		
	Iridium (ppb)	<50	Neutron Activation	
	Iron (%)	7.9	Analyses and Fusion /	
	Lanthanum	24	XRF Analyses are	
	Lutetium	0.436	single results and are	
	Mercury	nr	indicative only. These	
	Molybdenum	<10	are provided for matrix	
	Neodymium	nr	identification purposes.	
	Nickel	40		
	Potassium (%)	nr		
	Rubidium	80	'nr': Not Reported	
	Samarium	5.4		
	Scandium	23.4		
	Selenium	<10		
	Silver	<5		
	Sodium (%)	1.94		
	Strontium	nr		
	Tantalum	<2		
	Tellurium	<20		
	Terbium	<1		
	Thorium	11.2		
	Tin	<200		
	Tungsten	<5		
	Uranium	7		
	Ytterbium	3		
	Zinc	1270		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website http://www.geostats.com.au

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: