Common Seal

GEOSTATS PTY LTD


Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM316-7

Certified Control Values

Total Digest



Partial Digest

· ··· ·· · · · · · · · · · · · · · · ·							
Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval			
Nickel (ppm)	774	56	63	+/- 14.1			
Copper (ppm)	2716	136	81	+/- 30.3			
Zinc (ppm)	40	7	58	+/- 1.8			
Lead (ppm)	8	3	49	+/- 0.7			
Arsenic (ppm)	42	4	57	+/- 1			
Cobalt (ppm)	51	5	66	+/- 1.4			
Silver (ppm)	0.6	0.3	48	+/- 0.1			

CRM Details

	Neutron Activation		Major Elements by	
Control Statistic Details	Analysis Results (ppm,		Fusion / XRF (%)	
Control statistics were produced from results accumulated in the April-2016	unless otherwi	se noted)		
round robin. The number of results used to certify each analyte is shown in the	Antimony	11.6	Fe	4.73
table above.	Arsenic	46	SiO ₂	46.69
	Barium	130	Al ₂ O ₃	0.52
Material Description	Bromine	<2	TiO ₂	0.022
This material is described as an Acurite and Malachite, with Carbonate, Quartz,	Cadmium	<10	MnO	0.184
Talc and Fuchsite ex Turkey.	Caesium	<1	CaO	13.55
	Calcium (%)	nr	Р	0.003
Colour Designation (ISCC-NBS, SP440)	Cerium	<10	S	0.095
This material is grayish orange in colour.	Chromium	1870	MgO	9.3
	Cobalt	57	K ₂ O	0.057
Usage	Europium	<0.5	Na ₂ O	0.037
This product is for use in the mining industry as a reference material for	Gold (ppb)	<10	LOI1000	21.52
monitoring and testing the accuracy of laboratory assaying.	Hafnium	<5		
	Iridium (ppb)	<50	Neutron Act	ivation
Preparation and Packaging	Iron (%)	4.5	Analyses and Fusion /	
All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry	Lanthanum	1	XRF Analyses are	
material is then pulverised to better than 75 micron (nominal mean of 45 micron)	Lutetium	< 0.05	single results and are	
using an air classifier. The material is then homogenised and stored in a sealed,	Mercury	nr	· ·	
stable container ready for final packaging.	Molybdenum	<10	indicative only. These	
	Neodymium	nr	are provided	d for matrix
Materials are statistically sampled from stores, then packaged into either heat	Nickel	840	identification	n purposes.
sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready	Potassium (%)	nr		
for distribution. All packaging has been chosen to ensure minimal contamination	Rubidium	<20	'nr': Not Rep	orted
from outside sources during shipment, use and storage.	Samarium	<0.2		
	Scandium	3.3		
Assay Testwork	Selenium	<10		
All standards are tested thoroughly in the Geostats bi-annual laboratory survey.	Silver	<5		
This involves assaying by multiple laboratories from around the world. Results	Sodium (%)	0.049		
are compiled into a comprehensive report detailing statistics for each standard.	Strontium	nr		
Assay distributions are checked and processed statistically, producing	Tantalum	<2		
monitoring statistics for these standards. Materials are tested regularly to ensure	Tellurium	<20		
stability and homogeneity.	Terbium	<1		
	Thorium	<0.5		
<u>Stability</u>	Tin	<200		
This product remains stable in its original packaging, away from direct sunlight.	Tungsten	<5		
	Uranium	<1		
Material Safety	Ytterbium	<1		
This product is not hazardous and non-toxic.	Zinc	<100		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163 Phone: +61 8 9314 2566, Fax: +61 8 9314 3699 e-mail: pjh@geostats.com.au, srr@geostats.com.au Website http://www.geostats.com.au