


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Ore Grade Base Metal Reference Material Product Code

GBM320-13

Certified Control Values



GBM320-13

Geostats Pty Ltd, Certified Ore Grade Base Metal Reference Material, Product Code:

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	71	7	75	+/- 2
Copper (ppm)	504	24	97	+/- 5
Zinc (ppm)	190189	6720	84	+/- 1467
Lead (ppm)	49252	1457	86	+/- 314
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	47.7	1.7	103	+/- 0.32
Sulphur (%)	10.77	0.33	84	+/- 0.07

CRM Details

<u>Control Statistic Details</u> Control statistics were produced from results accumulated in the April-2020 round robin. The number of results used to certify each analyte is shown in the table above.	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	<u>Material Description</u> This material is described as a Zinc Sulphide Ore Composite.	Antimony	524	Fe
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is pale brown in colour.	Arsenic	63	SiO ₂	50.67
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Barium	<100	Al ₂ O ₃	3.16
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Bromine	4	TiO ₂	0.26
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cadmium	838	MnO	0.04
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Caesium	5	CaO	0.68
<u>Material Safety</u> This product is not hazardous and non-toxic.	Calcium (%)	nr	P	0.036
	Cerium	22	S	10.76
	Chromium	104	MgO	0.67
	Cobalt	80	K ₂ O	0.74
	Europium	1.2	Na ₂ O	0.26
	Gold (ppb)	595	LOI1000	9.36
	Hafnium	<5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Iridium (ppb)	<50	'nr': Not Reported	
	Iron (%)	3.8		
	Lanthanum	6		
	Lutetium	<0.2		
	Mercury	nr		
	Molybdenum	<10		
	Neodymium	nr		
	Nickel	64		
	Potassium (%)	nr		
	Rubidium	29		
	Samarium	1.5		
	Scandium	5.5		
	Selenium	<10		
	Silver	48		
	Sodium (%)	0.113		
	Strontium	nr		
	Tantalum	<2		
	Tellurium	<20		
	Terbium	<1		
	Thorium	2.1		
	Tin	<200		
	Tungsten	13		
	Uranium	<2		
	Ytterbium	<0.5		
	Zinc	192000		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 | Email: info@geostats.com.au

Website: www.geostats.com.au