

# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

## GBM900-3

Certified Control Values



GBM900-3

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code:

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	34345	1651	91	+/- 345.8
Copper (ppm)	16681	558	114	+/- 104
Zinc (ppm)	714	43	112	+/- 8.2
Lead (ppm)	873	50	112	+/- 9.5
Arsenic (ppm)	319	26	94	+/- 5.3
Cobalt (ppm)	150	11	92	+/- 2.3
Silver (ppm)	7.5	0.9	108	+/- 0.2

### CRM Details

<u>Control Statistic Details</u> Control statistics were produced from results accumulated in the October-2000 & April-2008 round robins. The number of results used to certify each analyte is shown in the table above.	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	<u>Material Description</u> This material is described as a Sulphide Ore.	Antimony	10.75	Fe
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light brownish gray in colour.	Arsenic	341.5	SiO <sub>2</sub>	nr
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Barium	61	Al <sub>2</sub> O <sub>3</sub>	nr
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Bromine	<0.5	TiO <sub>2</sub>	nr
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cadmium	<5	MnO	nr
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Caesium	6.895	CaO	nr
<u>Material Safety</u> This product is not hazardous and non-toxic.	Calcium (%)	1.59	P	nr
	Cerium	28.7	S	nr
	Chromium	371	MgO	nr
	Cobalt	152	K <sub>2</sub> O	nr
	Europium	0.54	Na <sub>2</sub> O	nr
	Gold (ppb)	12750	LOI1000	nr
	Hafnium	11.05		
	Iridium (ppb)	<50	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Iron (%)	5.875	'nr': Not Reported	
	Lanthanum	16.8		
	Lutetium	<0.2		
	Mercury	nr		
	Molybdenum	36.45		
	Neodymium	nr		
	Nickel	34500		
	Potassium (%)	1.39		
	Rubidium	267		
	Samarium	2.035		
	Scandium	8.1		
	Selenium	8		
	Silver	9		
	Sodium (%)	0.884		
	Strontium	nr		
	Tantalum	110		
	Tellurium	<10		
	Terbium	<0.5		
	Thorium	5.95		
	Tin	<100		
	Tungsten	17.55		
	Uranium	6.7		
	Ytterbium	1.13		
	Zinc	727		
	Zirconium	624		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>