

# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

## GBM901-6

Certified Control Values



GBM901-6

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code:

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	91	12	56	+/- 3.2
Copper (ppm)	214816	6511	62	+/- 1667
Zinc (ppm)	148	14	56	+/- 3.8
Lead (ppm)	3269	171	63	+/- 43.4
Arsenic (ppm)	248	26	53	+/- 7.2
Cobalt (ppm)	328	29	58	+/- 7.7
Silver (ppm)	43.7	4.4	65	+/- 1.1

### CRM Details

<u>Control Statistic Details</u> Control statistics were produced from results accumulated in the October-2001 round robin. The number of results used to certify each analyte is shown in the table above.	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	<u>Material Description</u> This material is described as a Copper Ore.	Antimony	<0.5	Fe
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is medium dark gray in colour.	Arsenic	264	SiO <sub>2</sub>	nr
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Barium	176	Al <sub>2</sub> O <sub>3</sub>	nr
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Bromine	<1	TiO <sub>2</sub>	nr
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cadmium	nr	MnO	nr
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Caesium	21.5	CaO	nr
<u>Material Safety</u> This product is not hazardous and non-toxic.	Calcium (%)	<1	P	nr
	Cerium	86.6	S	nr
	Chromium	58.1	MgO	nr
	Cobalt	344	K <sub>2</sub> O	nr
	Europium	0.85	Na <sub>2</sub> O	nr
	Gold (ppb)	89400	LOI1000	nr
	Hafnium	9.86		
	Iridium (ppb)	<20	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Iron (%)	9.55	'nr': Not Reported	
	Lanthanum	51.1		
	Lutetium	0.48		
	Mercury	nr		
	Molybdenum	<10		
	Neodymium	nr		
	Nickel	nr		
	Potassium (%)	1.47		
	Rubidium	698		
	Samarium	6.91		
	Scandium	10.7		
	Selenium	<10		
	Silver	45.1		
	Sodium (%)	1.48		
	Strontium	nr		
	Tantalum	<2		
	Tellurium	22.7		
	Terbium	nr		
	Thorium	6.77		
	Tin	nr		
	Tungsten	58.6		
	Uranium	5.28		
	Ytterbium	3.81		
	Zinc	145		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>