


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Ore Grade Base Metal Reference Material Product Code

GBM911-16

Certified Control Values



GBM911-16

Geostats Pty Ltd, Certified Ore Grade Base Metal Reference Material, Product Code:

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	229	nr	nr	nr
Copper (ppm)	24774	871	199	+/- 122
Zinc (ppm)	1210	56	171	+/- 9
Lead (ppm)	325	nr	nr	nr
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	7.9	1.0	173	+/- 0.14
Sulphur (%)	3.62	0.17	142	+/- 0.03

CRM Details

<u>Control Statistic Details</u> Control statistics were produced from results accumulated in the October-2011 & April-2012 round robins. The number of results used to certify each analyte is shown in the table above.	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	<u>Material Description</u> This material is described as a Cu / Gold Sulphide ore.	Antimony	4.75	Fe
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is medium light gray in colour.	Arsenic	311.5	SiO ₂	59.13
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Barium	475	Al ₂ O ₃	12.43
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Bromine	<0.5	TiO ₂	0.897
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cadmium	<5	MnO	0.07
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Caesium	2.45	CaO	3.28
<u>Material Safety</u> This product is not hazardous and non-toxic.	Calcium (%)	nr	P	0.053
	Cerium	54.5	S	3.65
	Chromium	80	MgO	1.7
	Cobalt	316	K ₂ O	2.7
	Europium	1.05	Na ₂ O	3.224
	Gold (ppb)	13000	LOI1000	2.77
	Hafnium	8.85		
	Iridium (ppb)	<10	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Iron (%)	7.125	'nr': Not Reported	
	Lanthanum	31.8		
	Lutetium	0.43		
	Mercury	nr		
	Molybdenum	52		
	Neodymium	nr		
	Nickel	270		
	Potassium (%)	nr		
	Rubidium	125		
	Samarium	4.8		
	Scandium	12.9		
	Selenium	7		
	Silver	6.5		
	Sodium (%)	2.39		
	Strontium	nr		
	Tantalum	1.35		
	Tellurium	<10		
	Terbium	0.85		
	Thorium	18.4		
	Tin	<100		
	Tungsten	4.5		
	Uranium	10.8		
	Ytterbium	3.05		
	Zinc	1205		
	Zirconium	280		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>