


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Ore Grade Base Metal Reference Material Product Code

GBM916-11



Certified Control Values

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	9	6	40	+/- 2
Copper (ppm)	10864	324	251	+/- 40
Zinc (ppm)	60894	2386	211	+/- 325
Lead (ppm)	2843	123	217	+/- 16
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	68.0	4.2	236	+/- 0.54
Sulphur (%)	9.89	0.30	181	+/- 0.04

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the October-2016, April-2018 round robins. The number of results used to certify each analyte is shown in the table above.	Antimony	64.9	Fe
Material Description This material is described as a Zn / Cu / Ag Sulphide ex Armenia.	Arsenic	242	SiO ₂	54.55
	Barium	231	Al ₂ O ₃	7.79
Colour Designation (ISCC-NBS, SP440) This material is medium gray in colour.	Bromine	<2	TiO ₂	0.17
	Cadmium	508.5	MnO	0.3
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	<1	CaO	3.77
	Calcium (%)	nr	P	0.014
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	<10	S	9.74
	Chromium	<10	MgO	1.44
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	8	K ₂ O	1.2
	Europium	1.73	Na ₂ O	0.39
Stability This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	3915	LOI1000	6.38
	Hafnium	<5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
Material Safety This product is not hazardous and non-toxic.	Iridium (ppb)	<50	'nr': Not Reported	
	Iron (%)	7		
	Lanthanum	4.04		
	Lutetium	0.23		
	Mercury	nr		
	Molybdenum	<10		
	Neodymium	nr		
	Nickel	<20		
	Potassium (%)	nr		
	Rubidium	21		
	Samarium	1.55		
	Scandium	10.8		
	Selenium	11		
	Silver	62		
	Sodium (%)	0.434		
	Strontium	nr		
	Tantalum	<2		
	Tellurium	53.8		
	Terbium	<1		
	Thorium	<0.5		
	Tin	<200		
	Tungsten	<5		
	Uranium	1		
	Ytterbium	1.2		
	Zinc	61750		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website <http://www.geostats.com.au>

GBM916-11

Geostats Pty Ltd, Certified Ore Grade Base Metal Reference Material, Product Code: