


GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM917-3

Certified Control Values



GBM917-3

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	5	2	46	+/- 0.5
Copper (ppm)	54	7	65	+/- 1.6
Zinc (ppm)	175	8	63	+/- 2
Lead (ppm)	28	3	63	+/- 0.8
Arsenic (ppm)	42	5	50	+/- 1.5
Cobalt (ppm)	18	2	66	+/- 0.5
Silver (ppm)	4.8	0.6	62	+/- 0.16

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	5	2	40	+/- 0.6
Copper (ppm)	54	6	63	+/- 1.5
Zinc (ppm)	165	11	63	+/- 2.8
Lead (ppm)	27	4	58	+/- 1.1
Arsenic (ppm)	41	7	57	+/- 1.9
Cobalt (ppm)	17	2	44	+/- 0.5
Silver (ppm)	4.7	0.5	71	+/- 0.12

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)	Major Elements by Fusion / XRF (%)	
		Fe	5.1
Control statistics were produced from results accumulated in the October-2017 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony 4.1	SiO ₂	60.19
Material Description This material is described as a Low grade sulphide ore ex Laos.	Arsenic 40.2	Al ₂ O ₃	16.69
Colour Designation (ISCC-NBS, SP440) This material is very light gray in colour.	Barium 875	TiO ₂	0.635
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Bromine <2	MnO	0.203
Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium <10	CaO	0.973
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Caesium 16	P	0.09
Stability This product remains stable in its original packaging, away from direct sunlight.	Calcium (%) nr	S	0.552
Material Safety This product is not hazardous and non-toxic.	Cerium 43	MgO	2.25
	Chromium 6	K ₂ O	7.7
	Cobalt 17	Na ₂ O	0.5
	Europium 1.1	LOI1000	3.26
	Gold (ppb) 288	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
	Hafnium <5	'nr': Not Reported	
	Iridium (ppb) <50		
	Iron (%) 5.1		
	Lanthanum 22		
	Lutetium 0.3		
	Mercury nr		
	Molybdenum <10		
	Neodymium nr		
	Nickel <20		
	Potassium (%) nr		
	Rubidium 283		
	Samarium 4		
	Scandium 17.4		
	Selenium <10		
	Silver <5		
	Sodium (%) 0.37		
	Strontium nr		
	Tantalum <2		
	Tellurium <20		
	Terbium 1		
	Thorium 8.6		
	Tin <200		
	Tungsten 12		
	Uranium 2		
	Ytterbium 2.2		
	Zinc <200		
	Zirconium <500		

20 Hines Road, O'Connor, Western Australia 6163
Phone : +61 8 9314 2566, Fax : +61 8 9314 3699
e-mail : pjh@geostats.com.au, srr@geostats.com.au
Website http://www.geostats.com.au

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: