Common Sea

## **GEOSTATS PTY LTD**


**Mining Industry Consultants Reference Material Manufacture and Sales** 

Certified Geochem Base Metal Reference Material Product Code

## **GBM921-8**

# Certified Control Values

#### **Total Digest**



## **Partial Digest**

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	20	2	54	+/- 0.6
Copper (ppm)	6942	198	80	+/- 44.3
Zinc (ppm)	20885	842	54	+/- 232
Lead (ppm)	6640	391	65	+/- 97.7
Arsenic (ppm)	75	8	63	+/- 2
Cobalt (ppm)	31	3	61	+/- 0.7
Silver (ppm)	45.4	2.5	79	+/- 0.56

#### **CRM Details**

	Neutron Activation		Major Elements by	
Control Statistic Details	Analysis Results (ppm,		Fusion / XRF (%)	
Control statistics were produced from results accumulated in the October-2021	unless otherwi			()
round robin. The number of results used to certify each analyte is shown in the	Antimony	26.5	Fe	6.09
table above.	Arsenic	82	SiO <sub>2</sub>	54.19
	Barium	380	Al <sub>2</sub> O <sub>3</sub>	13.28
Material Description	Bromine	<2	TiO <sub>2</sub>	3.044
This material is described as a High Grade Silver ore.	Cadmium	56.8	MnO	0.12
, and the second	Caesium	2	CaO	5.6
	Calcium (%)	nr	Р	0.056
Colour Designation (ISCC-NBS, SP440)	Cerium	38	S	2.24
This material is light gray in colour.	Chromium	124	MgO	3.25
	Cobalt	47	K <sub>2</sub> O	1.82
Usage	Europium	1.4	Na <sub>2</sub> O	3.058
This product is for use in the mining industry as a reference material for	Gold (ppb)	578	LOI1000	1.55
monitoring and testing the accuracy of laboratory assaying.	Hafnium	7		
	Iridium (ppb)	<50	Neutron Act	ivation
Preparation and Packaging	Iron (%)	6.5	Analyses ar	d Fusion /
All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry	Lanthanum	20	XRF Analyses are	
material is then pulverised to better than 75 micron (nominal mean of 45	Lutetium	0.4	single results and are	
micron) using an air classifier. The material is then homogenised and stored in	Mercury	nr	Ŭ	
a sealed, stable container ready for final packaging.	Molybdenum	96	indicative only. These	
	Neodymium	nr	are provided	d for matrix
Materials are statistically sampled from stores, then packaged into either heat	Nickel	43	identification	n purposes.
sealed, air tight, plastic pulp packets or screw top sealed plastic containers	Potassium (%)	nr		
ready for distribution. All packaging has been chosen to ensure minimal	Rubidium	81	'nr': Not Rep	orted
contamination from outside sources during shipment, use and storage.	Samarium	4.5		
	Scandium	20.3		
Assay Testwork	Selenium	<10		
All standards are tested thoroughly in the Geostats bi-annual laboratory survey.	Silver	48		
This involves assaying by multiple laboratories from around the world. Results	Sodium (%)	2.2		
are compiled into a comprehensive report detailing statistics for each standard.	Strontium	nr		
Assay distributions are checked and processed statistically, producing	Tantalum	4		
monitoring statistics for these standards. Materials are tested regularly to	Tellurium	<20		
ensure stability and homogeneity.	Terbium	1		
	Thorium	11.9		
<u>Stability</u>	Tin	<200		
This product remains stable in its original packaging, away from direct sunlight.	Tungsten	10		
	Uranium	6		
Material Safety	Ytterbium	2.7		
This product is not hazardous and non-toxic.	Zinc	21700		
	Zirconium	< 500	l	

20 Hines Road, O'Connor, Western Australia 6163 Phone: +61 8 9314 2566 | Email: info@geostats.com.au Website: www.geostats.com.au