


# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales

Certified Ore Grade Base Metal Reference Material Product Code

## GBM922-13

Certified Control Values



Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	52	11	87	+/- 2
Copper (ppm)	10050	375	203	+/- 52
Zinc (ppm)	931	60	114	+/- 11
Lead (ppm)	176	18	109	+/- 3
Cobalt (ppm)	nr	nr	nr	nr
Silver (ppm)	3.5	0.5	100	+/- 0.09
Sulphur (%)	1.52	0.08	157	+/- 0.01

### CRM Details

		Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
<b><u>Control Statistic Details</u></b> Control statistics were produced from results accumulated in the October-2022, October-2010 round robins. The number of results used to certify each analyte is shown in the table above.		Antimony	2.3	Fe	6.21
		Arsenic	124	SiO <sub>2</sub>	59.4
		Barium	413	Al <sub>2</sub> O <sub>3</sub>	13.45
		Bromine	<2	TiO <sub>2</sub>	1.184
		Cadmium	<10	MnO	0.11
		Caesium	3	CaO	5.85
		Calcium (%)	nr	P	0.062
		Cerium	43	S	1.58
		Chromium	99	MgO	3.06
		Cobalt	150	K <sub>2</sub> O	1.87
		Europium	1.2	Na <sub>2</sub> O	3.038
		Gold (ppb)	5790	LOI1000	1.13
		Hafnium	<5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.  'nr': Not Reported	
		Iridium (ppb)	<50		
		Iron (%)	7.1		
		Lanthanum	23		
		Lutetium	0.4		
		Mercury	nr		
		Molybdenum	<10		
		Neodymium	nr		
		Nickel	<100		
		Potassium (%)	nr		
		Rubidium	88		
		Samarium	5		
		Scandium	19.7		
		Selenium	6		
		Silver	<5		
		Sodium (%)	2.21		
		Strontium	nr		
		Tantalum	<2		
		Tellurium	<20		
		Terbium	<1		
		Thorium	12.9		
		Tin	<200		
		Tungsten	4		
		Uranium	7		
		Ytterbium	2.9		
		Zinc	940		
		Zirconium	<500		
<b><u>Material Description</u></b> This material is described as a Copper Ore sulphide.					
<b><u>Colour Designation (ISCC-NBS, SP440)</u></b> This material is medium light gray in colour.					
<b><u>Usage</u></b> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.					
<b><u>Preparation and Packaging</u></b>  All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.					
<b><u>Assay Testwork</u></b> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.					
<b><u>Stability</u></b> This product remains stable in its original packaging, away from direct sunlight.					
<b><u>Material Safety</u></b> This product is not hazardous and non-toxic.					

20 Hines Road, O'Connor, Western Australia 6163  
Phone: +61 8 9314 2566 | Email: [info@geostats.com.au](mailto:info@geostats.com.au)  
Website: [www.geostats.com.au](http://www.geostats.com.au)

GBM922-13

Geostats Pty Ltd, Certified Ore Grade Base Metal Reference Material, Product Code: