Major Elements

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Multi-Element Reference Material Product Code

GBMS623-3

Certified Control Values

<u> </u>	<u>n</u>	<u>a</u>	ıy	<u>S</u>	<u>e</u>	<u>s</u>	
							_

Element	Grade	Standard Deviation	No of Analyses	Confidence Interval
Au - FA (ppm)	5.85	0.39	99	+/- 0.079
Au - AR (ppm)	5.46	0.44	64	+/- 0.112
Silver (ppm)	3.7	0.8	181	+/- 0.12
Copper (ppm)	10792	537	204	+/- 74.3
Lead (ppm)	322	24	187	+/- 3.5
Zinc (ppm)	35	7	184	+/- 1.1
Nickel (ppm)	77	10	183	+/- 1.5
Arsenic (ppm)	570	54	177	+/- 8
Cobalt (ppm)	332	30	175	+/- 4.6
Sulphur (%)	5.16	0.22	131	+/- 0.038

CRM Details

Control Statistic Details

Control statistics were produced from results accumulated in the :

 $\frac{\text{Oct-98, Apr-00, Apr-06}}{\text{64}} \qquad \text{Geostats Pty Ltd Laboratory Round Robin Programs.}$

Source Material

Prior to homogenisation and testing, this material was sourced from Copper/Gold ore oxide ex Pilbara region.

Colour Designation

Light brownish gray

<u>Usage</u>

This product is for use in the mining industry as reference materials for monitoring and testing the accuracy of laboratory assaying.

Preparation and Packaging

All standards are dried in an oven for a minimum of 12 hours at 110C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. Thematerial is then homogenised and stored in a sealed, stable container ready for final packaging.

Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.

Assay Testwork

All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by a minimum of 50 reputable laboratories selected from across the world using a variety of methods (including FA, AR, 3AD, 4AD and ICP, AAS and XRF). Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and



Intention Activa	Major Elements		
Analysis Resul	ts (ppm)	Fusion / XRF (%)	
Antimony	2	Fe	nr
Arsenic	558	SiO2	nr
Barium	<100	Al2O3	nr
Bromine	7	TiO2	nr
Cadmium	nr	MnO	nr
Cerium	206	CaO	nr
Caesium	<1	Р	nr
Chromium	496	S	nr
Cobalt	356	MgO	nr
Europium	1	K20	nr
Gold ppb	5400	Na2O	nr
Hafnium	7	LOI1000	nr
Iridium ppb	<20		
Iron %	6		
Lanthanum	113		
Lutetium	1		
Molybendum	<5		
Nickel	nr		
Rubidium	41		
Samarium	14		
Scandium	22		
Selenium	<5		
Sodium %	1		
Tantalum	<1		
Tellurium	<5		
Terbium	nr		
Thorium	10		
Tin	nr		
Tungsten	129		
Uranium	<2		
Ytterbium	4		
Zinc	<100		
Zirconium	<500		
Calcium%	8		
Potassium %	1		
Silver	<5		
Mercury	nr		
Neodymium	nr		
Strontium	nr		

Neutron Activation

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 e-mail: info@geostats.com.au Website http://www.geostats.com.au