

## Certified Pulp Iron Ore Reference Material - GIOP-39

### Certificate of Analysis

Analyte	Units	Average	Standard Deviation	Count	95% Confidence Interval
Fe	%	56.61	0.19	50	+/- 0.05
Fe (Calc)	%	56.6	0.11	47	+/- 0.03
SiO <sub>2</sub>	%	5.875	0.044	50	+/- 0.013
Al <sub>2</sub> O <sub>3</sub>	%	2.606	0.042	50	+/- 0.012
TiO <sub>2</sub>	%	0.1518	0.0052	50	+/- 0.0015
Mn	%	0.0757	0.0039	49	+/- 0.0011
CaO	%	0.1465	0.0046	50	+/- 0.0013
P	%	0.0396	0.0019	49	+/- 0.0005
S	%	0.0123	0.0023	39	+/- 0.0008
MgO	%	0.153	0.012	49	+/- 0.004
K <sub>2</sub> O	%	0.01	0.0017	39	+/- 0.0005
Zn	%	0.007	0.0015	38	+/- 0.0005
Pb	%	0.0042			
Cu	%	0.0026	0.0013	31	+/- 0.0005
Ba	%	0.0024			
V	%	0.0026	0.0012	37	+/- 0.0004
Cr	%	0.0034			
Cl	%	0.0054			
As	%	0.0017			
Ni	%	0.003	0.0023	30	+/- 0.0009
Co	%	0.0021	0.0016	34	+/- 0.0006
Sn	%	0.0017			
Sr	%	0.0017			
Zr	%	0.0036			
Na	%	0.014			
LOI <sub>425</sub>	%	8.774	0.041	30	+/- 0.015
LOI <sub>650</sub>	%	9.5	0.092	37	+/- 0.031
LOI	%	9.757	0.097	45	+/- 0.029

#### Control Statistic Details

Control values for this material were determined during a certification program.

#### Certification Date

This material was certified with the above values on:

1/09/2010

#### Source Material

Prior to homogenisation and testing, this material was sourced from  
 Pilbara

#### Usage

10A Marsh Close, O'Connor  
Western Australia 6163  
Phone +618 93142566 Fax +618 93143699  
Email [info@geostats.com.au](mailto:info@geostats.com.au)  
Website <http://www.geostats.com.au>

**GEOSTATS PTY LTD**

Mining Industry Consultants  
Reference Material Manufacture and Sales

This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.

#### **Preparation and Packaging**

This certified reference material was dried in an oven for a minimum of 8 hours at 105°C. The dry material was pulverised in a "puck and bowl" and then homogenised in a vee-blender. The material is then packaged into 10g plastic packets, ready for shipment.

#### **Certification Testwork**

This certified reference material was tested in a dedicated certification program. 10 samples were sent to 5 laboratories for XRF analyses. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.