

# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales


## Certified Low Level Gold Reference Material Product Code

# GLG314-3

## Certified Control Values

### Low Level Gold

Gold Grade 103.11 ppb  
Standard Deviation 7.02 ppb  
Confidence Interval +/- 1.51 ppb



## CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	Control statistics were produced from results accumulated in the April-2014 round robin. A total of 87 gold assays were used to certify this material.	Antimony	0.1	Fe
<u>Material Description</u> This material is described as a Milled Mine Waste.	Arsenic	55	SiO <sub>2</sub>	52.06
	Barium	170	Al <sub>2</sub> O <sub>3</sub>	14.99
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is light olive gray in colour.	Bromine	<0.5	TiO <sub>2</sub>	1.92
	Cadmium	<5	MnO	0.17
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	<0.5	CaO	9.54
	Calcium (%)	nr	P	0.102
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	28	S	0.076
	Chromium	210	MgO	5.36
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	52	K <sub>2</sub> O	0.37
	Europium	2	Na <sub>2</sub> O	2.91
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	120	LOI1000	0.08
	Hafnium	5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
<u>Material Safety</u> This product is not hazardous and non-toxic.	Iridium (ppb)	<50	nr: Not Reported	
	Iron (%)	8.8		
	Lanthanum	11		
	Lutetium	0.5		
	Mercury	nr		
	Molybdenum	76		
	Neodymium	nr		
	Nickel	61		
	Potassium (%)	nr		
	Rubidium	<10		
	Samarium	6.4		
	Scandium	33.7		
	Selenium	<5		
	Silver	1.94		
	Sodium (%)	2.26		
	Strontium	nr		
	Tantalum	0.6		
	Tellurium	nr		
	Terbium	1.4		
	Thorium	0.9		
	Tin	nr		
	Tungsten	<1		
	Uranium	<0.5		
	Ytterbium	4		
	Zinc	220		
	Zirconium	nr		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

GLG314-3

Geostats Pty Ltd, Certified Low Level Gold Reference Material, Product Code: