

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales


Certified Low Level Gold Reference Material Product Code

GLG314-4

Certified Control Values

Low Level Gold

Gold Grade 51.39 ppb
Standard Deviation 4.13 ppb
Confidence Interval +/- 0.9 ppb



CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>	<u>Major Elements by Fusion / XRF (%)</u>	
Control statistics were produced from results accumulated in the April-2014 round robin. A total of 84 gold assays were used to certify this material.	Antimony 0.1	Fe	1.36
	Arsenic 31	SiO ₂	74.72
	Barium 570	Al ₂ O ₃	12.9
	Bromine <1.2	TiO ₂	0.2
	Cadmium <5	MnO	0.03
	Caesium 3.7	CaO	1.23
	Calcium (%) nr	P	0.019
	Cerium 49	S	0.036
	Chromium 30	MgO	0.75
	Cobalt 45	K ₂ O	4.14
	Europium 1	Na ₂ O	3.29
	Gold (ppb) 60	LOI1000	0.69
	Hafnium 4	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes. 'nr': Not Reported	
	Iridium (ppb) <50		
	Iron (%) 1.4		
	Lanthanum 28		
	Lutetium <0.2		
	Mercury nr		
	Molybdenum 47		
	Neodymium nr		
	Nickel 116		
	Potassium (%) nr		
	Rubidium 230		
	Samarium 3.1		
	Scandium 4.1		
	Selenium <5		
	Silver <2		
	Sodium (%) 2.59		
	Strontium nr		
	Tantalum 2.7		
	Tellurium nr		
	Terbium 0.7		
	Thorium 25.1		
	Tin nr		
	Tungsten <1		
	Uranium 17.3		
	Ytterbium 2		
	Zinc <100		
	Zirconium nr		
<u>Material Description</u> This material is described as a Milled Mine Waste.			
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is very light gray in colour.			
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.			
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.			
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.			
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.			
<u>Material Safety</u> This product is not hazardous and non-toxic.			

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

GLG314-4

Geostats Pty Ltd, Certified Low Level Gold Reference Material, Product Code: