

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales


Certified Low Level Gold Reference Material Product Code

GLG911-3

Certified Control Values

Low Level Gold

Gold Grade	3.74 ppb
Standard Deviation	2.84 ppb
Confidence Interval	+/- 0.95 ppb



CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	Control statistics were produced from results accumulated in the October-2011 round robin. A total of 38 gold assays were used to certify this material.	Antimony	<0.2	Fe
<u>Material Description</u> This material is described as a Fresh Bunbury basalt.	Arsenic	<0.2	SiO ₂	51.89
	Barium	180	Al ₂ O ₃	14.75
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is medium gray in colour.	Bromine	<0.5	TiO ₂	1.897
	Cadmium	<5	MnO	0.16
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	0.4	CaO	9.71
	Calcium (%)	nr	P	0.091
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	24	S	0.053
	Chromium	190	MgO	5.46
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	40	K ₂ O	0.387
	Europium	1.9	Na ₂ O	2.944
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	<2	LOI1000	0.23
	Hafnium	3.7	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
<u>Material Safety</u> This product is not hazardous and non-toxic.	Iridium (ppb)	<20	'nr': Not Reported	
	Iron (%)	8.5		
	Lanthanum	9.9		
	Lutetium	0.49		
	Mercury	nr		
	Molybdenum	<5		
	Neodymium	nr		
	Nickel	38		
	Potassium (%)	nr		
	Rubidium	13		
	Samarium	5.3		
	Scandium	33.2		
	Selenium	<5		
	Silver	<2		
	Sodium (%)	2.13		
	Strontium	nr		
	Tantalum	0.5		
	Tellurium	<10		
	Terbium	1.2		
	Thorium	1.2		
	Tin	<200		
	Tungsten	<2		
	Uranium	0.2		
	Ytterbium	3.3		
	Zinc	130		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

GLG911-3

Geostats Pty Ltd, Certified Low Level Gold Reference Material, Product Code: