

# GEOSTATS PTY LTD

Mining Industry Consultants  
Reference Material Manufacture and Sales


## Certified Low Level Gold Reference Material Product Code

# GLG914-5

## Certified Control Values

### Low Level Gold

Gold Grade 195.97 ppb  
Standard Deviation 10.30 ppb  
Confidence Interval +/- 1.54 ppb



## CRM Details

<u>Control Statistic Details</u>	<u>Neutron Activation Analysis Results (ppm, unless otherwise noted)</u>		<u>Major Elements by Fusion / XRF (%)</u>	
	Control statistics were produced from results accumulated in the October-2014 & April-2015 round robins. A total of 176 gold assays were used to certify this material.	Antimony	0.1	Fe
<u>Material Description</u> This material is described as a Milled Tail material.	Arsenic	<1	SiO <sub>2</sub>	68.715
	Barium	600	Al <sub>2</sub> O <sub>3</sub>	13.295
<u>Colour Designation (ISCC-NBS, SP440)</u> This material is very light gray in colour.	Bromine	<0.5	TiO <sub>2</sub>	0.67
	Cadmium	<5	MnO	0.07
<u>Usage</u> This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.	Caesium	4.085	CaO	3.64
	Calcium (%)	nr	P	0.041
<u>Preparation and Packaging</u> All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.  Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cerium	55.3	S	0.031
	Chromium	60	MgO	1.685
<u>Assay Testwork</u> All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.	Cobalt	13.5	K <sub>2</sub> O	3.15
	Europium	0.952	Na <sub>2</sub> O	3.25
<u>Stability</u> This product remains stable in its original packaging, away from direct sunlight.	Gold (ppb)	210.5	LOI1000	0.525
	Hafnium	4.5	Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.	
<u>Material Safety</u> This product is not hazardous and non-toxic.	Iridium (ppb)	<50	nr: Not Reported	
	Iron (%)	3.35		
	Lanthanum	31.95		
	Lutetium	0.3		
	Mercury	nr		
	Molybdenum	<2		
	Neodymium	nr		
	Nickel	10.9		
	Potassium (%)	nr		
	Rubidium	155		
	Samarium	3.775		
	Scandium	11.8		
	Selenium	<10		
	Silver	<1		
	Sodium (%)	2.53		
	Strontium	nr		
	Tantalum	1.8		
	Tellurium	nr		
	Terbium	0.8		
	Thorium	22.7		
	Tin	nr		
	Tungsten	<1		
	Uranium	10.8		
	Ytterbium	2		
	Zinc	65		
	Zirconium	nr		

20 Hines Road, O'Connor, Western Australia 6163

Phone : +61 8 9314 2566, Fax : +61 8 9314 3699

e-mail : pjh@geostats.com.au, srr@geostats.com.au

Website <http://www.geostats.com.au>

GLG914-5

Geostats Pty Ltd, Certified Low Level Gold Reference Material, Product Code: