Major Elements by

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Low Level Gold Reference Material Product Code

GLG923-5

Certified Control Values

Low Level Gold

Gold Grade 165.03 ppb

Standard Deviation 10.95 ppb

Confidence Interval +/- 2.59 ppb



Neutron Activation

CRM Details

	Analysis Results (ppm,		Fusion / XRF (%)	
Control Statistic Details				
Control statistics were produced from results accumulated in the October-2023	unless otherwi		, ,	
round robin. A total of 72 gold assays were used to certify this material.	Antimony	6.1	Fe	12.3
	Arsenic	114	SiO ₂	47
	Barium	310	Al ₂ O ₃	12.75
Material Description	Bromine	<2	TiO ₂	0.7
This material is described as a Sulphide, Pilbara, WA.	Cadmium	<10	MnO	0.08
·	Caesium	8	CaO	3.25
	Calcium (%)	nr	Р	0.063
Colour Designation (ISCC-NBS, SP440)	Cerium	34	S	11.79
This material is medium light gray in colour.	Chromium	19	MgO	1.27
	Cobalt	32	K ₂ O	2.67
<u>Usage</u>	Europium	0.7	Na ₂ O	0.52
This product is for use in the mining industry as a reference material for	Gold (ppb)	174	LOI1000	13.05
monitoring and testing the accuracy of laboratory assaying.	Hafnium	<5		
	Iridium (ppb)	<50	Neutron Act	ivation
Preparation and Packaging	Iron (%)	12	Analyses and Fusion /	
All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry	Lanthanum	17	XRF Analyses are	
material is then pulverised to better than 75 micron (nominal mean of 45 micron)	Lutetium	0.2	single results and are	
using an air classifier. The material is then homogenised and stored in a sealed,	Mercury	nr	ŭ	
stable container ready for final packaging.	Molybdenum	<10	indicative only. These	
	Neodymium	nr	are provided	d for matrix
Materials are statistically sampled from stores, then packaged into either heat	Nickel	<100	identification purposes.	
sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready	Potassium (%)	nr		
for distribution. All packaging has been chosen to ensure minimal contamination	Rubidium	88	'nr': Not Rep	oorted
from outside sources during shipment, use and storage.	Samarium	2.9		
	Scandium	10.5		
Assay Testwork	Selenium	<10		
All standards are tested thoroughly in the Geostats bi-annual laboratory survey.	Silver	<5		
This involves assaying by multiple laboratories from around the world. Results	Sodium (%)	0.4		
are compiled into a comprehensive report detailing statistics for each standard.	Strontium	nr		
Assay distributions are checked and processed statistically, producing	Tantalum	<2		
monitoring statistics for these standards. Materials are tested regularly to ensure	Tellurium	<20		
stability and homogeneity.	Terbium	<1		
	Thorium	3.9		
Stability	Tin	<200		
This product remains stable in its original packaging, away from direct sunlight.	Tungsten	2		
	Uranium	1		
Material Safety	Ytterbium	1.4		
I This was discilled a set becaused as a set of a set to it.	17:		1	

20 Hines Road, O'Connor, Western Australia 6163
Phone: +61 8 9314 2566 | Email: info@geostats.com.au
Website: www.geostats.com.au

Zinc

Zirconium

602

<500

This product is not hazardous and non-toxic.