GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Reference Material Product Code

GMO-05

Certified Control Values

Element	Grade	Standard Deviation	No of Analyses	Confidence Interval
Molybdenum (ppm)	27.7	1.48	29	+/- 0.54
Copper (ppm)	639	40	133	+/- 6.7
Silver (ppm)	0.88	0.45	70	+/- 0.1
Lead (ppm)	13.4	5.2	97	+/- 1
Zinc (ppm)	87	9.0	111	+/- 1.7
Bismuth (ppm)	10.6	0.8	29	+/- 0.31
Arsenic (ppm)	12.7	3.33	75	+/- 0.8
Antimony (ppm)	0.47	0.05	29	+/- 0.02

CRM Details

Control Statistic Details

Control values for this material were determined during a dedicated certification program and the Geostats semiannual Round Robin.

Source Material

Prior to homogenisation and testing, this material was sourced from:

Basalt rock with trace mineralisation

Colour Designation

Light Gray

Usage

This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.

Preparation and Packaging

All reference materials are dried in an oven for a minimum of 12 hours at 110 °C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an Air Classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging.

Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic tubs ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.

Assay Testwork

This standard was thoroughly tested in a dedicated certification program. 10 samples of the product were analysed by 5 reputable laboratories. Additionally, a minimum of 50 reputable laboratories analysed a single sample in the Geostats semi-annual Round Robin. Results are compiled into a comprehensive report detailing statistics for the reference material. Assay distributions are checked and processed statistically, producing monitoring statistics for the product. Materials are tested regularly to ensure stability and homogeneity.

10A Marsh Close, O'Connor, Western Australia 6163 Phone: +61 8 9314 2566, Fax: +61 8 9314 3699 e-mail: pjh@geostats.com.au, jcm@geostats.com.au

Website http://www.geostats.com.au