

GEOSTATS PTY LTD

Mining Industry Consultants
Reference Material Manufacture and Sales

Certified Geochem Base Metal Reference Material Product Code

GBM325-1



Certified Control Values

Total Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	22	2	54	+/- 0.5
Copper (ppm)	57	4	58	+/- 1.1
Zinc (ppm)	106	4	54	+/- 1.1
Lead (ppm)	11	2	50	+/- 0.6
Arsenic (ppm)	141	6	50	+/- 1.8
Cobalt (ppm)	16	1	53	+/- 0.3
Silver (ppm)	0.4	0.2	31	+/- 0.07

Partial Digest

Element	Grade	Standard Deviation	Num of Analyses	Confidence Interval
Nickel (ppm)	22	2	52	+/- 0.5
Copper (ppm)	57	5	71	+/- 1.1
Zinc (ppm)	101	5	56	+/- 1.2
Lead (ppm)	9	2	46	+/- 0.5
Arsenic (ppm)	133	7	50	+/- 1.9
Cobalt (ppm)	16	1	52	+/- 0.3
Silver (ppm)	0.4	0.1	45	+/- 0.04

CRM Details

Control Statistic Details	Neutron Activation Analysis Results (ppm, unless otherwise noted)		Major Elements by Fusion / XRF (%)	
	Control statistics were produced from results accumulated in the April-2025 round robin. The number of results used to certify each analyte is shown in the table above.	Antimony	12.5	Fe
Material Description This material is described as a Low grade sulphide - Pilbara, Western Australia.	Arsenic	143	SiO ₂	63.21
	Colour Designation (ISCC-NBS, SP440) This material is very light gray in colour.	Barium	307	Al ₂ O ₃
Usage This product is for use in the mining industry as a reference material for monitoring and testing the accuracy of laboratory assaying.		Bromine	<2	TiO ₂
	Preparation and Packaging All CRMs are dried in an oven for a minimum of 12 hours at 110°C. The dry material is then pulverised to better than 75 micron (nominal mean of 45 micron) using an air classifier. The material is then homogenised and stored in a sealed, stable container ready for final packaging. Materials are statistically sampled from stores, then packaged into either heat sealed, air tight, plastic pulp packets or screw top sealed plastic containers ready for distribution. All packaging has been chosen to ensure minimal contamination from outside sources during shipment, use and storage.	Cadmium	<10	MnO
Assay Testwork All standards are tested thoroughly in the Geostats bi-annual laboratory survey. This involves assaying by multiple laboratories from around the world. Results are compiled into a comprehensive report detailing statistics for each standard. Assay distributions are checked and processed statistically, producing monitoring statistics for these standards. Materials are tested regularly to ensure stability and homogeneity.		Caesium	7	CaO
	Stability This product remains stable in its original packaging, away from direct sunlight.	Calcium (%)	nr	P
Material Safety This product is not hazardous and non-toxic.		Cerium	46	S
	CRM Details	Chromium	30	MgO
Neutron Activation Analyses and Fusion / XRF Analyses are single results and are indicative only. These are provided for matrix identification purposes.		Cobalt	17	K ₂ O
	'nr': Not Reported	Europium	1.2	Na ₂ O
Gold (ppb)		15	LOH1000	5.46
	Hafnium	<5		
Iridium (ppb)		<50		
	Iron (%)	4.6		
Lanthanum		23		
	Lutetium	0.3		
Mercury		nr		
	Molybdenum	<10		
Neodymium		nr		
	Nickel	<100		
Potassium (%)		nr		
	Rubidium	85		
Samarium		4.1		
	Scandium	12.6		
Selenium		<10		
	Silver	<5		
Sodium (%)		1.09		
	Strontium	nr		
Tantalum		<2		
	Tellurium	<20		
Terbium		1		
	Thorium	7		
Tin		<200		
	Tungsten	3		
Uranium		1		
	Ytterbium	2		
Zinc		<200		
	Zirconium	<500		

20 Hines Road, O'Connor, Western Australia 6163

Phone: +61 8 9314 2566 | Email: info@geostats.com.au

Website: www.geostats.com.au

GBM325-1

Geostats Pty Ltd, Certified Geochem Base Metal Reference Material, Product Code: